

Product Specifications	Units	Values	Test Methods
<b>Material - 10x8 Silver/Black</b>			
Count	10x8	1450 denier	ASTM D 751-2000
Weight	5.25 oz		
Tensile Strength Warp	210		
Tensile Strength Filling	192		
Elongation at Breakage (Grab method, CRE Type)			
Warp	16,5		
Filling	15,8		
Tear Strength (Single tongue method), LBS			
Warp	65		
Filling	63		
Bursting Strength (Diaphragm method) psi	368,4		

Product Specifications	Units	Values	Test Methods
<b>Material - Clear</b>			
Count	10x8	900 denier	
Weight	3.6 oz		
Coating Thickness	1.0-1.25		
Tensile Strength Grab			
Tensile Strength Grab			
UV Weathering		Not exposed under mesh cover	
Tapes per sq. Inch (Double Tarp)	10x8		
Field Seams	Sewn		
Heat Sealed Seams	Either		
Domestic/Foreign material source	Foreign		
Country of Origin	China		